

L Number	Hits	Search Text	DB	Time stamp
1	168	yamamoto near1 michiharu	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:30
2	1	nonaka near1 tositeru	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:31
3	2	umegaki near1 takahiro	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:31
4	168	(yamamoto near1 michiharu) (nonaka near1 tositeru) (umegaki near1 takahiro)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:31
5	99695	(titanium Ti) same (copper Cu)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:31
6	76108	(copper Cu) near1 (alloy base based remain remaining balanced balancing rest)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:32
7	10202	((titanium Ti) same (copper Cu)) same ((copper Cu) near1 (alloy base based remain remaining balanced balancing rest))	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:33
8	389515	aging aged harden hardened	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:33
9	1120	((((titanium Ti) same (copper Cu)) same ((copper Cu) near1 (alloy base based remain remaining balanced balancing rest))) and (aging aged harden hardened)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:33
10	11273	grain and bending	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:34
11	83	(((((titanium Ti) same (copper Cu)) same ((copper Cu) near1 (alloy base based remain remaining balanced balancing rest))) and (aging aged harden hardened)) and (grain and bending)	USPAT; US-PGPUB; EPO; JPO; DERWENT	2004/02/07 14:34